



UNIVERSITAT POLITÈCNICA
DE CATALUNYA
BARCELONATECH



Swansea University
Prifysgol Abertawe



Centrale
Nantes

AIRBUS
GROUP

VOLKSWAGEN

AKTIENGESELLSCHAFT

SIEMENS



Marie Skłodowska-Curie Actions
Innovative Training Networks
European Training Network
number 675919
AdMoRe project

Influence of the residual stresses in reshaping operations of large aeronautical parts

Ramiro MENA
AIRBUS
École Centrale de Nantes (ECN)
Universitat Politècnica de Catalunya (UPC)

November 22-23, 2017. CM3, Brussels

Marie Skłodowska-Curie
ITN-ETN

AdMoRe

UNIVERSITAT POLITÈCNICA
DE CATALUNYA
BARCELONA

Swansea University
Porthgoleu Aberdare

Centrale
Nantes

FAIRBOS
GROUP

VOLKSWAGEN
AKTIENGESellschaft

SIEMENS

esi

Motivation of the project

Residual stresses

- Definition and Types
- Formulation

Distortion

- How it is produced

Register for free at <https://www.scipedia.com> to download the version without the watermark

Reshaping

- Influence of Residual Stresses
- Experiment
- Challenges

Conclusions and future works

Motivation of the project

Context

Large and thick aeronautical parts present distortion after machining because the residual stresses (RS) generated during previous manufacturing steps (heat treatment).

Before assembly, distortion is removed manually.

It is a time consuming operation and depends exclusively on the skills of a well trained operator.

Register for free at <https://www.scipedia.com> to download the version without the watermark

Scientific goals

- To develop a Reduced Order Model (ROM) for reshaping
- To evaluate the main parameters during the process and its uncertainty level

Industrial goals

- To study reshaping from a numerical perspective
- To adapt reshaping simulations to each warped geometry
- To introduce numerical simulation in order to assist the operator

Residual Stresses

Definition

“Residual Stresses in a body are those which are not necessary to maintain equilibrium between the body and its environment”
(Whiters and Bhadeshia, 2001)

Types

Type I: Macro stresses (our goal)

Type II: Intergranular stresses

Type III: Atomic scale

Formulation

$$\sigma = \sigma^r + \sigma^l \quad (1)$$


$$\varepsilon = \varepsilon^r + \varepsilon^l$$

$$\sigma^r = \mathbf{D} \cdot (\varepsilon^r - \varepsilon^0)$$

$$\varepsilon^r = \varepsilon^0 + \varepsilon_r^0 \quad (2)$$

$$= \varepsilon^0 + \mathbf{C} \cdot \sigma^r, \mathbf{C} = \mathbf{D}^{-1}$$

Fig. Strain and stress decomposition with initial prestrain
(J. Holniewski-Szulc and Z. Mroz, 1997)



Distortion: How it is produced (1/4)

Problem statement

What? To produce numerically distortion and to study reshaping

Research question

What is the influence of RS for reshaping ?

- RS order of magnitude: ± 30 MPa (Robinson et al., 2014)
- for simple geometries (e.g rectangular plates)

Proposal :

To compare a deformed part with and without RS

- Geometry : T shaped beam
- Reshaping : four point bending operation
- Material : AA7010




Fig. Four point bending test scheme

Distortion: How it is produced (2/4)

Methodology

What? To produce numerically distortion and to study reshaping

How? To simulate all the manufacturing chain.

- Two study cases: $M_o=10$ and 5mm (Machining offset M_o)





Fig. T-shaped beam geometry (top). Sequential simulation approach (bottom)

Distortion: How it is produced (3/4)

Residual stress evolution




Fig. RS evolution during a) Quenching ($\sigma_{y1}=162$ MPa). b) Machining: case 1 and c) Machining: case 2 ($\sigma_{y2}=390$ MPa). Note : The snapshots are taken in plane $Z=0$ and presented in the undeformed configuration

Distortion: How it is produced (4/4)

Warped geometry

Distortion δ as a function of RS and machining offset (Mo)

$$\delta = f(RS, Mo)$$

Type 1 (Longitudinal)

Type 2 (Wings closure)





Fig.

Distortion δ as a function of Machining offset (Mo)

a) δ type 1 and 2 for Mo=10mm

b) δ type 1 and 2 for Mo= 5mm



Reshaping: Influence of RS (1/3)

Reshaping

Two study groups :

- Beam with Residual Stresses (RS)
- Beam without Residual Stress (RSF)

Three configurations for each machining case

Machining Offset Mo(mm)	10			5		
Position ID	P1	P2	P3	P4	P5	P6
Top (mm)	150	300	150	425	425	300
Bottom (mm)	425	425	300	150	300	150

Register for free at <https://www.scipedia.com> to download the version without the watermark

Contact : Rigid supports with friction $\mu=0.05$ (Koc et al., 2006)




Fig. Reshaping setup. Location of top and bottom supports

Reshaping: Influence of RS (2/3)

Comments

Reshaping as an optimization problem

Each position presents its own optimum stroke Y_s where δ is minimized.

There is an offset between the RS and RSF system.

A geometrical tolerance is required to validate possible configurations

Distortion can be minimized but not totally removed





Fig. Distortion evolution as a function of the given stroke Y_s . Left) $M_o=10\text{mm}$ and Right) $M_o=5\text{mm}$

Reshaping: Influence of RS (3/3)

Marie Skłodowska-Curie
ITN-ETN

AdMoRe



RS vs RSF system : distortion level

RSF hypothesis is able to mimic the distortion evolution of RS system.

Initial distortion measurement of the whole system is the key.

(+) Variability between two different pieces will be collected in the deformed shape.

(-) A calibration step will be required to determine the offset.




Fig. Distortion evolution along Z axis for configuration P1 and different Strokes Y_s
Left) Residual Stresses (RS). Centre) Residual Stresses Free (RSF). Right) Detail: minimized distortion

Reshaping: Experiment (1/2)

Marie Skłodowska-Curie
ITN-ETN

AdMoRe



Goals

To study reshaping in a controlled environment

To test the selected material model (Chaboche)

Problem setup

AA 7010T7451

General dimensions: 200x60x20 mm

Imposed vertical stroke $Y_s = \pm 9.5$ mm (x3)




Fig. Four point bending test. Experimental setup (left), Beam 's cross section (right)

Reshaping: Experiment (2/2)

Marie Skłodowska-Curie
ITN-ETN

AdMoRe



Swansea University
Prifysgol Abertawe

Centrale
Nantes

AIRBUS
GROUP

VOLKSWAGEN
AKTIENGESellschaft

SIEMENS



Results





Fig. Four point bending test. Strain Gauge J1(left), Strain Gauge J2 (right). RSF (top), RS (bottom)

Reshaping: Challenges

Marie Skłodowska-Curie
ITN-ETN

AdMoRe



Reshaping simulation: Main ingredients

An efficient and adaptative algorithm

An accurate material model

Simulation error as a snow ball

Each simplification hypothesis introduces error in our results

How can I trust in my numerical results?

How to quantify the level of error?

Reshaping is done iteratively...




Fig. Connection between Residual Stresses, Distortion and Reshaping

Conclusions and future works

Marie Skłodowska-Curie
ITN-ETN

AdMoRe



Summary of the results

- Sequential simulation of Reshaping
- Influence of RS during reshaping
- Chaboche material model validation
- Awareness of simplification hypothesis

Ongoing and future investigations

- Do we need to simulate a complete 3D model?
- Model Order Reduction for reshaping (SSL method)

Expected outcome

- Numerical methodology to study reshaping
- Virtual demonstrator (computational vademecum)

Impact of the work from the academic and/or industrial POV

- Guided reshaping operation
- Productivity increment at workshop level
- Virtual manufacturing training environment

References

Marie Skłodowska-Curie
ITN-ETN

AdMoRe



P. J. Withers and H. K. D. H. Bhadeshia, Residual stress Part 1 – Measurement techniques, *Mat. Sci. Tech.* 17 (2001) 355-365.

J. Holnieki-Szule and Z. Mroz, Active Control of Stresses and Deflections of Elastic Structures by Means of Imposed Distortions, H. H. E. Leipholz (ed.), *Structural Control* (1987) 297-317

P. Jeanmart, J. Bouvaist, Finite element calculation and measurement of thermal stresses in quenched plates of high strength 7075 aluminium alloy, *Mat. Sci. Tech.* 1 (1985) 765–769.

D.A. Tanner, J.S. Robinson, Modelling stress reduction techniques of cold compression and stretching in wrought aluminium alloy products, *Finite Elem. Anal. Des.* 39 (2003) 369–386.

F. Chinesta, A. Leygue, F. Bordeu, J.V. Aguado, E. Cueto, D. Gonzalez, I. Alfaro, A. Ammar, and A. Huerta. PGD-based Computational Vademecum for efficient design, optimization and control. *Arch. Comput. Methods Eng.*, 20 (2013) 31–59.

J.S. Robinson, D.A. Tanner, C.E. Truman, 50th Anniversary Article : The Origin and Management of Residual Stress in Heat-treatable Aluminium Alloys, *Strain* 50 (2014) 185–207.

M. Koc, J. Culp, T. Altan, Prediction of residual stresses in quenched aluminum blocks and their reduction through cold working processes, *J. Mater. Process. Tech.* 174 (2006) 342-354.